



0756



Engineering Services Laboratory

Radnor Road, Scorrier, Redruth TR16 5EH
TEL : 01872 327381 FAX : 01209 821539

SOIL WPSD TEST REPORT

Scheme / Site: **Chenoweth trading - Materials testing**
 Location: **Recycled material stockpile**
 Material: **6F2 Earthworks Coarse Material- Capping Layer**
 Specification: **DTp Spec for H/Way Works Table 6/1 Class 6F2**
 Source: **Recycled Material**
 Sample Type: **Bulk**
 Location / Orientation of Sample to Original: **Unknown**
 Soil Description, Disturbance & Condition: **Recycled concrete**
 Prep Method of Sampling: **Wet-sieve**
 Date Sampled: **10/10/2019** Sampled By: **CLT**
 Date Received: **11/10/2019** Departure from BS: **None**


Date Tested: **01/11/2019** Tested By: **JR**

Tested To : BS 1377:Pt 2:1990:Md 9.2

Sieve	Passing %	Specification
125mm	100	100
90mm	100	80 - 100
75mm	100	65 - 100
37.5mm	85	45 - 100
20mm	39	
10mm	22	15 - 60
6.3mm	18	
5mm	16	10 - 45
600µm	7	0 - 25
63µm	2	0 - 12

Test Report No:	AG1739
Ticket No.	0518
Project No:	31549
Order Number	-----
Date Reported:	01/11/2019
Page 1 of 1	

Test	Result	Specification
Moisture Content(%):	5.2	
Uniformity Coefficient:		



Moisture Content in accordance with BS 1377: Pt 2: 1990 Md 3.2
 Uniformity Coefficient in accordance with BS EN ISO 14688-2: 2004 Cl. 3.2

Remarks : **Sample complies with sampling and analysis requirements.**

Client Name: **Chenoweths Trading Company LTD**
 F.A.O: **Guy T**
 Address: **Unit 6**
Chenoweths Business Park
Ruan Highlands
Truro
TR2 5JT

Authorised Signatory:

G Nye
 Senior Laboratory Technician
 Cormac Solutions Ltd